



Environmental Product Declaration



THE INTERNATIONAL EPD® SYSTEM



In accordance with ISO 14025:2006 and EN 15804:2012+A2:2019 for:

Reinforcing Steel Bar Gerdau CA-60, Welded Mesh and Truss

URS (Sapucaia do Sul) and Fabrication Shop (Pirituba)
facilities

From

GERDAU ACOS LONGOS S.A.



GERDAU
Shape the future

Programme:

Programme operator:

EPD registration number:

Publication date:

Valid until:

The International EPD® System EPD registered through the fully aligned regional programme: Hub EPD Brasil. More information at www.environdec.com


EPD International AB, Regional Hub: EPD Brasil. www.environdec.com

S-P-08842

2023-05-19

2028-05-09

An EPD should provide current information and may be updated if conditions change. The stated validity is therefore subject to the continued registration and publication at www.environdec.com



Contents

General information	3
Programme information.....	3
Company information: Gerdau Corporation and Operations in Brazil	4
Owner of the EPD	4
Contact	4
Description of the organization.....	4
Product-related or management system-related certifications	4
Name and location of production site(s).....	4
Product information: Reinforcing Steel Bar Gerdau CA-60, Welded Mesh, Truss and Column Mesh.....	6
Product name	6
Product identification.....	6
Product description	6
Content declaration.....	8
UN CPC code.....	8
Geographical scope	8
LCA information: Life Cycle Impact Assessment	9
Declared unit.....	9
Reference service life	9
Time representativeness	9
Database(s) and LCA software used.....	9
Description of system boundaries.....	9
Adopted premises to fill data gaps.....	9
Environmental performance indicators	13
Mandatory impact category indicators according to EN 15804.....	13
Additional mandatory and voluntary impact category indicators	14
Resource use indicators	14
Waste indicators.....	15
Output flow indicators	15
Information on biogenic carbon content	15
Other environmental performance indicators	16
Additional environmental information	17
References.....	18

General information

Programme information

Programme:	The International EPD [®] System. More information at www.environdec.com
Address:	EPD International AB Box 210 60 SE-100 31 Stockholm Sweden
Website:	www.environdec.com
E-mail:	info@environdec.com
Brazilian Hub:	<u>Fundação Vanzolini</u>
Address:	<u>Rua Camburiú, 255 Alto da Lapa, São Paulo (SP) 05058-020</u>
Website:	<u>www.epdbrasil.com.br</u>
E-mail:	<u>epdbrasil@vanzolini.com.br</u>

Accountabilities for PCR, LCA and independent, third-party verification
Product Category Rules (PCR)
CEN standard EN 15804 serves as the Core Product Category Rules (PCR)
Product Category Rules (PCR): <i>PCR 2019:14 version 1.11 (Construction Products) and UN CPC Code 4124 - Bars and rods, hot-rolled, of iron or steel</i>
PCR review was conducted by: <i>Claudia A. Peña from ADDERE Research & Technology. Mobile: +56 9 9359 9210. E-mail: cpena@addere.cl</i>
Life Cycle Assessment (LCA)
LCA accountability: <i>Carolina Alves, Thays Sampaio, Peter Shonfield, Augusto Mello; ERM Brasil Ltda.</i>
Third-party verification
Independent third-party verification of the declaration and data, according to ISO 14025:2006, via:
<input checked="" type="checkbox"/> EPD verification by individual verifier
Third-party verifier: Edivan Cherubini. Mobile:+551195694-7217. E-mail: edivan@enciclo.com.br
Approved by: The International EPD [®] System

The EPD owner has the sole ownership, liability, and responsibility for the EPD.

EPDs within the same product category but from different programmes may not be comparable. EPDs of construction products may not be comparable if they do not comply with EN 15804. For further information about comparability, see EN 15804 and ISO 14025.

Company information: Gerdau Corporation and Operations in Brazil

Owner of the EPD

GERDAU ACOS LONGOS S.A.

Contact

Av. das Nações Unidas, 8.501 - 6º andar – São Paulo Municipality, São Paulo State, Brazil
Naiara Lopes <naiara.lopes@gerdau.com.br>

Description of the organization

With a history spanning 122 years, Gerdau is Brazil's largest and one of the leading producers of long steel in the Americas and of special steel in the world. In Brazil, Gerdau produces flat steel and iron ore for its own use. Gerdau also has a new business division, Gerdau Next, which fosters entrepreneurship in segments adjacent to the steel industry. Guided by its purpose of empowering people who build the future, Gerdau has operations in nine countries and over 30 000 direct and indirect employees. Gerdau is the largest recycling company in Latin America and uses scrap as an important input, with 71% of the steel it produces made from scrap. Every year, Gerdau transforms 11 million tonnes of scrap into a variety of steel products. Gerdau also is the world's largest charcoal producer, with over 250 hectares of planted forests in the state of Minas Gerais. As a result of its sustainable production matrix, Gerdau currently has one of the industry's lowest average greenhouse gas emissions (CO₂e). Gerdau's shares are listed on the São Paulo (B3), New York (NYSE) and Madrid (Latibex) stock exchanges.

Faced with an increasingly growing scenario for sustainable / green buildings and the requirements in relation to the products used in these types of constructions, Gerdau felt the need to start the certification of its products, in order to become competitive in this market in relation to its competitors. To achieve this goal, a Life Cycle Assessment (LCA) from cradle-to-gate was performed to support the preparation of EPD.

Product-related or management system-related certifications

All the products in this study follow the specifications of the ABNT NBR 7480 standards: Steel bars and wires for concrete reinforcement that provides definitions regarding bar and wire diameters, tolerances, geometric configurations (ribs), mechanical properties, identification, and test methods; and also, the specifications of ABNT NBR 6118: Design of concrete structures - Procedure. CA60 has compulsory certification by INMETRO. Furthermore, the producing plants have ISO 14001 – Environmental Management Systems and ISO 9001 - Quality Management System certification that certifies the ability to provide products and services that meet the requirements of customers, statutory, and applicable regulations, in order to increase customer satisfaction.

Name and location of production site(s)

- Gerdau Riograndense – Production of rebar
Location: Av. Borges de Medeiros, 650 - *Sapucaia do Sul Municipality, Rio Grande do Sul State, Brazil*
- Fabrication Shop – Cut and Bent products

For the production of cut and bent products, the rebars manufactured at Riograndense plant are then sent to the Fabrication Shops, which are located in other nineteen sites as shown in Table 1.

Table 1: Locations of Gerdau's fabrication shops that supply cut and bent rebars

Production Unit	State	City
SC1	CE	Maracanaú
SPE	PE	Cabo De Santo Agostinho
USB1	BA	Simoès Filho
ZAJ2	SE	Aracaju
ZMA2	AL	Maceio
ZTH2	PI	Teresina
CT1	MG	Contagem
CGD	RJ	Rio De Janeiro
GOI	GO	Aparecida De Goiânia
ZVIT	ES	Serra
ZCBA	MT	Cuiabá
PIR	SP	São Paulo
ZRPO	SP	Ribeirão Preto
UAR1	PR	Araucária
TIJ	SC	Tijucas
UFA	RS	Porto Alegre
ZXAP	SC	Chapeco
ZMAR	PR	Maringá
ZCGR	MS	Campo Grande

Product information: Reinforcing Steel Bar Gerdau CA-60, Welded Mesh, Truss and Column Mesh

Product name

Reinforcing Steel Bar Gerdau CA-60, Welded Mesh and Truss.

Product identification

Reinforcing Steel Bar Gerdau CA-60, welded meshes and trusses produced with low-carbon steel. The rebars are weldable, with ribbed surface and provided as rebar (in the following formats: straight bars, coils, and cut and bent bars), roll (spool), and welded trusses and meshes, presented in Table 2.

Table 2: URS CA60 products

Product	Step
Rebar	Wire drawing
Roll (Spool)	Cold Lamination
Welded Trusses	Trusses
Welded Meshes	Meshes

Product description

Reinforcing Steel Bar Gerdau CA-60 is rolled from wire machine and is used in a wide range of construction projects as the framework for reinforced concrete. The Gerdau CA-60 is the Gerdau brand for rebar produced in the CA60 category. The “60” is the specification of how much tensile stress the product must withstand without plastic deformation (600 MPa or 60 kgf / mm²). Moreover, the category CA60 is described in a standard. CA - Reinforced Concrete.

Tables 3, 4 and 5 represent the product technical specification and product composition.



Figure 1: Rebars produced by Gerdau

Table 3: Technical specification for rebar produced by Gerdau

Nominal Diameter (ND) (mm)	Nominal Mass (kg/m)	Linear Mass Tolerance (%)	Characteristic Flow Resistance (fy) (MPa)	Resistance Limit (MPa)	Elongation at 10 Ø	Pin Diameter for Folding at 180° (mm)
3.4	0.071	± 6%	600	1.05 x fy	5%	5 x DN
3.8	0.089	± 6%	600	1.05 x fy	5%	5 x DN
4.2	0.109	± 6%	600	1.05 x fy	5%	5 x DN
5	0.154	± 6%	600	1.05 x fy	5%	5 x DN
6	0.222	± 6%	600	1.05 x fy	5%	5 x DN
7	0.302	± 6%	600	1.05 x fy	5%	5 x DN
8	0.395	± 6%	600	1.05 x fy	5%	5 x DN

9.5	0.558	± 6%	600	1.05 x fy	5%	5 x DN
10	0.617	± 6%	600	1.05 x fy	5%	5 x DN

Table 4: Composition for rebar produced by Gerdau

Chemical composition	Quantity (%)
Iron	< 99
Manganese	< 0.7
Copper	< 0.35
Carbon	< 0.17
Others	< 0.92

Gerdau welded meshes are produced in accordance with the specifications and tolerances indicated in the ABNT NBR 7481 standard – Welded steel mesh – Reinforcement for concrete, with CA60 Gerdau steel wires or GG 50 Gerdau steel bars. The product is welded at all crossing points, connecting the wires and bars. It can be supplied in different configurations (size, spacing between wires, gauge, etc.) depending on the desired application. Welded meshes are usually supplied in 2.45m wide and 6m long panels or 2m wide by 3m long panels. In specific cases agreed with the customer, they can be produced in special dimensions.




Figure 2: Welded meshes produced by Gerdau

Gerdau trusses are made of ribbed CA-60 steel rebar and is supplied in lengths of 8, 10 and 12 meters. It can be found in heights from 6cm to 25cm. Gauges, heights and lengths other than those mentioned in the Table 6 can be provided upon prior consultation and customer/supplier agreement.



Figure 3: Trusses produced by Gerdau

Table 5: Technical specification for trusses produced by Gerdau

Gerdau Designation	Designation according to ABNT NBR 14859:3	Linear Mass Tolerance (%)	Height (cm)	Upper Chord (mm)	Diagonals (mm)	Lower Chord (mm)
TG 8 L	TR 08644	0.735	8	6.0	4.2	4.2
TG 8 M	TR 08645	0.821	8	6.0	4.2	5.0
TG 12 M	TR 12645	0.886	12	6.0	4.2	5.0
TG 12 R	TR 12646	1.016	12	6.0	4.2	6.0
TG 16 L	TR 16745	1.032	16	7.0	4.2	5.0
TG16R	TR 16746	1.168	16	7.0	4.2	6.0
TG 20 L	TR 20745	1.111	20	7.0	4.2	5.0
TG 20 R	TR 20756	1.446	20	7.0	5.0	6.0
TG 25 L	TR 25856	1.686	25	8.0	5.0	6.0

The application of each product is described below:

- Rebar: used in reinforced concrete structures, such as buildings, bridges, viaducts and other civil works to provide additional mechanical strength;
- Welded trusses: used to manufacture precast trussed slabs, trussed flat slabs, trussed mini panels and as a reinforcement spacer;
- Meshes: it is indicated for:
 - the construction of columns, beams, straps, baldrames, lintels, walls and also for the locking of walls; and
 - building slabs in reinforced concrete, industrial floors and precast structures, it is extremely practical because it comes ready-to-use.

Content declaration

Table 6: Dangerous substances from the candidate list of SVHC for Authorisation

Dangerous substances from the candidate list of SVHC for Authorisation	EC No.	CAS No.	Weight-% per functional or declared unit
Not applicable			

The structural steel does not require packaging, and none was considered in the present study.

No dangerous substances from the candidate list of SVHC for authorization are present in the composition of Reinforcing Steel Bar Gerdau CA-60, Welded Mesh and Truss.

UN CPC code

4124 - Bars and rods, hot-rolled, of iron or steel.

Geographical scope

Brazil

LCA information: Life Cycle Impact Assessment

Declared unit

The declared unit of this study is 1 metric ton of Reinforced Steel Bar Gerdau CA-60 (rebar, roll/ spoll), Welded Mesh and Truss, produced in Gerdau facility up to the gate.

Reference service life

Not applicable.

Time representativeness

Primary data for the core process was gathered for one year of operation (2019). Semi-annual data from 2019 was considered for the Fabrication Shop.

Database(s) and LCA software used

All primary data used was based on the manufacturer's specific data inventory. For consistency, the background life cycle inventory data from secondary sources used in this LCA were obtained from the databases contained within the Gabi 10.6.1.35 software; such as Gabi from Sphera 2020.1, Ecoinvent 3.7.1, USLCI and World Steel inventories 2021 (WSA 2021). Brazil specific data were preferably considered whenever available.

Description of system boundaries

This study is a cradle-to-gate (A1-A3) with modules C1-C4 and module D, carried out based on EN15804+A2 and the relevant PCR 2019:14 version 1.11 (Construction Products), which addresses the environmental aspects and potential environmental impacts from raw material acquisition to the point at which it leaves the gate of the URS facility (A3)/ Fabrication Shop (A3). The LCA also included the end-of-life stage, from the building de-construction/ demolition to the final disposal of the product of interest, and the potential benefits and loads beyond the system boundary, mandatory according to the PCR.

The life cycle stages descriptions are shown below in Figure 4. Modules declared, geographical scope, share of specific data (in GWP-GHG indicator) and data variation are presented in Table 7 (note that 'X' denotes inclusion in the LCA).

Adopted premises to fill data gaps

The following premises were considered in the study in order to fill data gaps:

- When specific transport distances from external suppliers to the factory were not available, a weighted average distance was used.
- When consumption data could not be directly measured in the plant, the input quantities were estimated based on the technical lists.
- At the manufacturing process in which disaggregated data was not available, physical allocation was performed to calculate the specific input values based on the production volumes and the total consumptions of the plant.




Figure 4: System boundary of the life cycle assessment for Reinforcing Steel Bar Gerdau CA-60, Welded Meshes and Trusses

The life cycle stages included within the system boundaries are:

- A1 – Primary raw material and alloys used for the manufacture of rebar;
- A2 – Includes the transportation of all raw materials and auxiliaries from suppliers to the Gerdau manufacturing facilities, as well as the outbound transportation to the Fabrication Shop;
- A3 – Scrap beneficiation, pig iron production, Melt Shop, Lamination, Wire Drawing, Cold Lamination, Fabrication Shop, transportation of all co-products/ wastes from Gerdau to the final destination and waste disposal;
- C1 – Manual dismantling of metal parts. Thus no environmental impact was attributed to the non-destructive removal of building waste in this module;
- C2 – Accounts for part of the waste processing, e.g. to a recycling site and transportation of waste e.g. to final sorting yard or disposal;
- C3 – It includes collection of waste fractions from the deconstruction and waste processing of material flows intended for reuse, recycling and energy recovery;
- C4 – Refers to waste disposal including physical pre-treatment and management of the disposal site; and
- D – Contains potential benefits and loads from the recycling of rebar considered in module C3 (95%).

The electricity mix considered for this LCA was based on the GaBi dataset for Brazil, which is representative of the Brazilian energy matrix for the reference year.

Table 7: Description of the system boundary according to the PCR

	Product stage			Construction process stage		Use stage							End of life stage				Resource recovery stage
	Raw material supply	Transport	Manufacturing	Transport	Construction installation	Use	Maintenance	Repair	Replacement	Refurbishment	Operational energy use	Operational water use	De-construction demolition	Transport	Waste processing	Disposal	Reuse-Recovery-Recycling-potential
Module	A1	A2	A3	A4	A5	B1	B2	B3	B4	B5	B6	B7	C1	C2	C3	C4	D
Modules declared	X	X	X	ND	ND	ND	ND	ND	ND	ND	ND	ND	X	X	X	X	X
Geography	BR	BR	BR	-	-	-	-	-	-	-	-	-	BR	BR	BR	BR	BR
Specific data used	>90%			-	-	-	-	-	-	-	-	-	-	-	-	-	-
Variation – products	9.6% ¹			-	-	-	-	-	-	-	-	-	-	-	-	-	-
Variation – sites	Not relevant			-	-	-	-	-	-	-	-	-	-	-	-	-	-

This EPD refers to multiple products. The scenarios included are currently in use and are representative for one of the most probable alternatives. Since the results for A1-A3 modules differed by less than $\pm 10\%$ for the GWP-GHG indicator, an average product composition was selected. In the following Table, the weighted average for each environmental impact indicator per declared unit are presented.²

¹ The percent variation of products was calculated based on the difference between the worst and the best-case products, in terms of the GWP-GHG indicator.

² The characterisation model and factors used in this study are in accordance with EN15804 for assessing the environmental impacts of construction products.

Environmental performance indicators³

Mandatory impact category indicators according to EN 15804

Table 8: Core environmental impact indicators

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
GWP-fossil	kg CO ₂ eq.	3.72E+02	5.41E+01	1.82E+02	6.08E+02	0.00E+00	2.36E+00	1.22E+00	2.44E+00	2.49E+02
GWP-biogenic	kg CO ₂ eq.	1.82E+00	-7.58E-01	-5.77E+00	-4.71E+00	0.00E+00	-3.31E-02	3.62E-03	-2.50E-02	1.42E-01
GWP-luluc	kg CO ₂ eq.	4.90E+00	4.46E+00	1.53E-01	9.51E+00	0.00E+00	1.95E-01	1.88E-02	2.44E-03	5.45E-03
GWP-total	kg CO ₂ eq.	3.78E+02	5.78E+01	1.77E+02	6.13E+02	0.00E+00	2.52E+00	1.24E+00	2.42E+00	2.49E+02
ODP	kg CFC 11 eq.	2.80E-06	1.27E-15	1.65E-06	4.45E-06	0.00E+00	5.53E-17	1.81E-08	5.77E-15	5.92E-13
AP	mol H ⁺ eq.	2.27E+00	1.74E-01	1.08E+00	3.53E+00	0.00E+00	7.61E-03	8.21E-03	7.78E-03	4.43E-01
EP-freshwater	kg PO ₄ ³⁻ eq.	2.21E-02	3.35E-04	2.78E+00	2.80E+00	0.00E+00	1.46E-05	9.65E-06	1.86E-06	5.41E-05
EP-freshwater	kg P eq.	6.77E-02	1.03E-03	8.53E+00	8.60E+00	0.00E+00	4.49E-05	2.96E-05	5.71E-06	1.66E-04
EP-marine	kg N eq.	4.00E-01	8.35E-02	2.36E+01	2.41E+01	0.00E+00	3.64E-03	1.63E-03	1.93E-03	8.54E-02
EP-terrestrial	mol N eq.	3.71E+00	8.74E-01	4.50E+00	9.08E+00	0.00E+00	3.81E-02	1.53E-02	2.12E-02	8.63E-01
POCP	kg NMVOC eq.	1.09E+00	1.52E-01	1.11E+00	2.35E+00	0.00E+00	6.62E-03	4.12E-03	6.08E-03	3.82E-01
ADP-minerals&metals	kg Sb eq.	2.69E-04	2.63E-06	8.48E-06	2.81E-04	0.00E+00	1.15E-07	1.99E-07	1.68E-07	6.18E-04
ADP-fossil	MJ	3.69E+03	7.26E+02	2.20E+03	6.61E+03	0.00E+00	3.17E+01	1.14E+01	3.56E+01	2.43E+03
WDP	m ³	1.15E+02	1.44E-01	-4.97E+03	-4.85E+03	0.00E+00	6.26E-03	3.36E-01	-2.89E-02	6.78E+02
Acronyms	GWP-fossil = Global Warming Potential fossil fuels; GWP-biogenic = Global Warming Potential biogenic; GWP-luluc = Global Warming Potential land use and land use change; ODP = Depletion potential of the stratospheric ozone layer; AP = Acidification potential, Accumulated Exceedance; EP-freshwater = Eutrophication potential, fraction of nutrients reaching freshwater end compartment; EP-marine = Eutrophication potential, fraction of nutrients reaching marine end compartment; EP-terrestrial = Eutrophication potential, Accumulated Exceedance; POCP = Formation potential of tropospheric ozone; ADP-minerals&metals = Abiotic depletion potential for non-fossil resources*; ADP-fossil = Abiotic depletion for fossil resources potential*; WDP = Water (user) deprivation potential, deprivation-weighted water consumption* *: The results of these environmental impact indicator shall be used with care as the uncertainties on these results are high or as there is limited experience with the indicator									

³ The estimated impact results are only relative statements which do not indicate the end points of the impact categories, exceeding threshold values, safety margins or risks.

Additional mandatory and voluntary impact category indicators

Table 9: GWP additional indicator

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
GWP-GHG ⁴	kg CO ₂ eq.	3.64E+02	5.27E+01	1.73E+02	5.89E+02	0.00E+00	2.30E+00	1.20E+00	2.29E+00	2.38E+02

Additional voluntary indicators e.g. the voluntary indicators from EN 15804 or the global indicators according to ISO 21930:2017

Resource use indicators

Table 10: Indicators describing resource use

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
PERE	MJ	5.02E+03	4.64E+01	9.80E+00	5.08E+03	0.00E+00	2.02E+00	1.85E+01	2.57E+00	-1.53E+02
PERM	MJ	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
PERT	MJ	5.02E+03	4.64E+01	9.80E+00	5.08E+03	0.00E+00	2.02E+00	1.85E+01	2.57E+00	-1.53E+02
PENRE	MJ	3.69E+03	7.26E+02	2.20E+03	6.62E+03	0.00E+00	3.17E+01	1.14E+01	3.56E+01	2.44E+03
PENRM	MJ.	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
PENRT	MJ	3.69E+03	7.26E+02	2.20E+03	6.62E+03	0.00E+00	3.17E+01	1.14E+01	3.56E+01	2.44E+03
SM	kg	1.09E+03	0.00E+00	6.72E+01	1.16E+03	0.00E+00	0.00E+00	0.00E+00	0.00E+00	-1.46E+02
RSF	MJ	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
NRSF	MJ	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
FW	m ³	2.16E+01	4.32E-02	-1.09E+02	-8.71E+01	0.00E+00	1.88E-03	7.99E-02	3.67E-04	1.58E+01
Acronyms	PERE = Use of renewable primary energy excluding renewable primary energy resources used as raw materials; PERM = Use of renewable primary energy resources used as raw materials; PERT = Total use of renewable primary energy resources; PENRE = Use of non-renewable primary energy excluding non-renewable primary energy resources used as raw materials; PENRM = Use of non-renewable primary energy resources used as raw materials; PENRT = Total use of non-renewable primary energy re-sources; SM = Use of secondary material; RSF = Use of renewable secondary fuels; NRSF = Use of non-renewable secondary fuels; FW = Use of net fresh water									

⁴ The indicator includes all greenhouse gases included in GWP-total but excludes biogenic carbon dioxide uptake and emissions and biogenic carbon stored in the product. This indicator is thus almost equal to the GWP indicator originally defined in EN 15804:2012+A1:2013.

Waste indicators

Table 11: Environmental information describing waste categories

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
Hazardous waste disposed	kg	2.23E-06	6.17E-09	1.59E-07	2.39E-06	0.00E+00	2.69E-10	8.37E-09	6.30E-09	-5.32E-07
Non-hazardous waste disposed	kg	2.39E+00	6.84E-02	2.33E+02	2.35E+02	0.00E+00	2.98E-03	7.65E-03	5.01E+01	-3.10E+01
Radioactive waste disposed	kg	1.31E-01	1.16E-04	7.83E-04	1.32E-01	0.00E+00	5.08E-06	4.55E-04	4.05E-04	-2.64E-04

Output flow indicators

Table 12: Indicators describing resource use

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
Components for re-use	kg	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Material for recycling	kg	8.98E-02	0.00E+00	1.92E+02	1.92E+02	0.00E+00	0.00E+00	9.50E+02	0.00E+00	0.00E+00
Materials for energy recovery	kg	0.00E+00	0.00E+00	1.95E+00	1.95E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Exported energy, electricity	MJ	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00
Exported energy, thermal	MJ	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00	0.00E+00

Information on biogenic carbon content

Table 13: Information describing the biogenic carbon content at the factory gate

Results per declared unit		
BIOGENIC CARBON CONTENT	Unit	QUANTITY
Biogenic carbon content in product	kg C	Around 0.17%
Biogenic carbon content in packaging	kg C	-

Note: 1 kg biogenic carbon is equivalent to 44/12 kg CO₂.

Structural steel does not use packaging, and none is modelled in the present study (the final product is labeled and grouped using wire bundles).

Other environmental performance indicators

Table 14: Additional environmental impact indicators

Results per declared unit										
Indicator	Unit	A1	A2	A3	Tot.A1-A3	C1	C2	C3	C4	D
PM	Disease incidences	2.77E-05	9.52E-07	6.77E-06	3.54E-05	0.00E+00	4.14E-08	1.13E-07	8.43E-08	8.42E-06
IR	kBq U235 eq.	1.10E+01	1.10E-02	5.59E-01	1.16E+01	0.00E+00	4.79E-04	3.38E-02	5.81E-02	-4.59E+00
ETF-fw	CTUe	2.97E+03	1.47E+03	3.97E+05	4.01E+05	0.00E+00	6.42E+01	4.83E+00	1.05E+01	1.57E+02
HTP-c	CTUh	2.09E-06	2.32E-08	4.35E-05	4.56E-05	0.00E+00	1.01E-09	7.83E-10	1.21E-09	1.35E-07
HTP-nc	CTUh	4.11E-06	7.24E-07	2.33E-03	2.33E-03	0.00E+00	3.16E-08	9.80E-09	1.23E-07	3.03E-06
SQP	Pt	2.84E+03	4.47E+02	3.89E+01	3.33E+03	0.00E+00	1.95E+01	9.62E+00	2.62E+00	-3.65E+01
Acronyms	PM = Particulate matter emissions; IR = Ionizing radiation, human health; ETF-fw = Eco-toxicity (freshwater); HTP-c = Human toxicity, cancer effects; HTP-nc = Human toxicity, non-cancer effects, SQP = Soil quality potential/ Land use related impacts									

Additional environmental information

The environment is a frequent topic at meetings of our Board of Directors and strategic committees. Our Sustainability Policy and Environmental Stewardship System reinforce our commitment to creating value for our stakeholders, and break down into measures to promote energy efficiency, reduce GHG emissions, water management, and reuse and recycle waste. They reinforce the company's commitment to creating value for its stakeholders, and are in line with global best practices and regulatory guidelines. These guidelines are cascaded to all company operations, and describe the procedures and responsibilities to be followed.

Gerdau is committed to being part of the solution to achieve a low-carbon economy, and has developed a medium and long term strategy to this end. For more information please check our commitment https://www2.gerdau.com.br/wp-content/uploads/2022/03/Gerdau_ING.pdf

References

ABNT NBR ISO 14040 - Environmental management - Life cycle assessment - Principles and framework, 2009.

ABNT NBR ISO 14044 - Environmental management – Life cycle assessment – Requirements and guidelines, 2009.

BS EN 15804:2012+A2:2019 - Sustainability of construction works. Environmental product declarations. Core rules for the product category of construction products.

Environmental profile of building elements, OVAM, 2020.

GaBi dataset <http://gabi-documentation-2020.gabi-software.com/xml-data/processes/1b8ba9d0-cf86-4029-b8c0-58a9a536b452.xml>.

General Programme Instructions of the International EPD[®] System. Version 3.01.

Hauschild M, G. M. (2011). Recommendations for Life Cycle Impact Assessment in the European context - based on existing environmental impact assessment models and factors. Luxembourg: European Commission.

ISO 14025 - Environmental labels and declarations - Type III environmental declarations - Principles and procedures, 2006.

Product Category Rule (PCR 2019:14 – version 1.11): “Construction products”, International EPD[®] System, 2019.

World Steel Association (WSA 2021) - Life cycle inventory (LCI) study - 2020 data release – Seventh global LCI study for steel products, 2021.

